



嘉时国际贸易（上海）有限公司
JWB INTERNATIONAL (SHANGHAI) CO., LTD
 上海市浦东新区启帆路515号南楼森兰美奂C809室
 C809, Mei Center, South Building, No. 515, Qifan Road,
 Pudong New Area, 201208 Shanghai, China
 TEL: 86-21-68888152 FAX: 86-21-68888153

Comparison List For Chemical Composition Of Titanium & Alloy

Alloy Composition	CHINA	AMERICAN	JPAN	GENMANY
	GB	UNS	JIS	DIN
Ti	TA 0	R50250/GR.1	1	3.7025
	TA1	R50400/GR.2	TP270	3.7035
	TA2	R50550/GR.3	TP340	3.7055
	TA3	R50700/GR.4	TP450	3.7065
	TA7	GR.6	=	3.7115
Ti-0.2Pb	TA9	R52400/GR.7	TP340Pb	3.7235
Ti-0.3Mo-0.8Ni	TA10	R53400/GR.12	=	3.7105
Ti-3Al-2.5V	TC2	R56320/GR.9	=	=
Ti-6Al-4V	TC4	R56400/GR.5	=	3.7175

From JWB Chinasourcing Technology
www.jwbchinasourcing.com